

CALCIUM CARBONATE MASTERBATCHES CREDOLEN®

Mark	Polymer base	CaCO ₃ , %	Bulk density, g/cm ³	MFI, g/10 min (190°, 5kg)	Application						
					PE films	Thin PE films	PE and PP pipes	Blow molding	PP fiber	Injection molding	Extrusion sheets
CPG 012	LLDPE	80	1,1±0,1	1-3	●	●		●	●		
CPG 033	LDPE / LLDPE	80	1,1±0,1	0,1-2,0	●	○	●	●	○	●	●
CPG 035	LDPE / LLDPE	80	1,1±0,1	0,1-2,0	○		●	○		●	●

● – recommended

○ – application possible after testing

Technocom LLC shall not be responsible for the use, accuracy and completeness of the information offered, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. Technocom LLC does not take any responsibility or liability for any information offered herein. The responsibility regarding the observance of third-party rights in the course of a subsequent processing and marketing of our products lies with the buyer.

